

1.0570 PDF-1 **St 52-3 / ~S355J1+N** Comprimento: 1000 mm

Aço plano de precisão com tolerância dimensional para maquinação

Espessura: + 0,4 / - 0 mm Comprimento: + 35 / - 0 mm Largura: + 0,4 / - 0 mm

Estado de fornecimento: max. 180 HB

Análise química

C: 0 – 0,22 Si: 0 – 0,55 Mn: 0 – 1,6 P: 0 – 0,035 S: 0 – 0,035

Espessura (mm)

Larg.	4,2	5,2	6,2	8,2	10,3	12,3	15,3	16,3	20,3	25,3	30,3	32,3	40,3	50,3	60,3	63,3	70,3	80,3	100,3	
10,3					x															
12,3						x														
15,3							x													
16,3								x												
20,3			x	x	x	x	x		x											
25,3	x	x	x	x	x	x	x	x	x	x										
30,3	x	x	x	x	x	x	x		x	x	x									
32,3	x	x	x	x	x	x		x	x	x		x								
40,3	x	x	x	x	x	x	x	x	x	x	x	x	x							
50,3	x	x	x	x	x	x	x	x	x	x	x	x	x	x						
60,3	x	x	x	x	x	x	x		x	x	x		x	x	x					
63,3	x	x	x	x	x	x	x	x	x	x		x	x	x		X				
70,3				x	x	x	x		x	x	x		x	x	x		X			
80,3	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	X	x	X		
100,3	x	x	x	X	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
120,3				X	x	x	x		x	x	x		x	x	x		x	x	x	
125,3	x	x	x	X	x	x	x	x	x	x	x	x	x	x	x	x		x	x	
140,3				x	x	x	x		x	x	x	x	x	x	x		x	x	x	
150,3	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x		x	x	
160,3	x	x	x	x	x	x	x	x	x	x	x	x	x	x		x		x	x	
175,3			x	x	x	x			x	x	x		x	x	x			x		
180,3				x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
200,3			x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
250,3			x	x	x	x	x	x	x	x	x	x	x	x	x	x		x	x	
300,3			x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
315,3			x	x	x	x		x	x	x		x	x	x		x		x	x	
350,3			x	x	x	x	x	x	x	x	x	x	x	x		x		x	x	
400,3	x	x	x	x	x	x	x	x	x	x		x	x	x		x		x	x	
450,3									x	x		x	x	x		x		x	x	
500,3									x	x		x	x	x		x		x	x	