

1.2083

PDF-2

X40Cr14

Comprimento: 500 mm

Espessura: + 0,4 / - 0 mm Comprimento: + 15 / - 0 mm Largura: + 3 / - 0 mm

Estado de fornecimento: max. 241 HB

Análise química

C: 0,36 – 0,42 Si: 0 – 1,0 Mn: 0 – 1,0 P: 0 – 0,03 S: 0 – 0,03

Cr: 12,5 – 14,5

Espessura (mm)

Larg.	2,3	3,3	4,3	5,3	6,3	8,3	10,3	12,3	15,3	20,3	25,3	30,3	40,3	50,3
33	X	X	X	X	X	X	X	X	X	X	X	X		
43	X	X	X	X	X	X	X	X	X	X	X	X	X	
53	X	X	X	X	X	X	X	X	X	X	X	X	X	X
63	X	X	X	X	X	X	X	X	X	X	X	X	X	X
73	X	X	X	X	X	X	X	X	X	X	X	X	X	X
83	X	X	X	X	X	X	X	X	X	X	X	X	X	X
93	X	X	X	X	X	X	X	X	X	X	X	X	X	X
103	X	X	X	X	X	X	X	X	X	X	X	X	X	X
123	X	X	X	X	X	X	X	X	X	X	X	X	X	X
143	X	X	X	X	X	X	X	X	X	X	X	X	X	X
153	X	X	X	X	X	X	X	X	X	X	X	X	X	X
163	X	X	X	X	X	X	X	X	X	X	X	X	X	X
183	X	X	X	X	X	X	X	X	X	X	X	X	X	X
203	X	X	X	X	X	X	X	X	X	X	X	X	X	X
223	X	X	X	X	X	X	X	X	X	X	X	X	X	X
243	X	X	X	X	X	X	X	X	X	X	X	X	X	X
253	X	X	X	X	X	X	X	X	X	X	X	X	X	X
263	X	X	X	X	X	X	X	X	X	X	X	X	X	X
283	X	X	X	X	X	X	X	X	X	X	X	X	X	X
303	X	X	X	X	X	X	X	X	X	X	X	X	X	X
323	X	X	X	X	X	X	X	X	X	X	X	X	X	X
343	X	X	X	X	X	X	X	X	X	X	X	X	X	X
353	X	X	X	X	X	X	X	X	X	X	X	X	X	X
363	X	X	X	X	X	X	X	X	X	X	X	X	X	X
383	X	X	X	X	X	X	X	X	X	X	X	X	X	X
403	X	X	X	X	X	X	X	X	X	X	X	X	X	X
423	X	X	X	X	X	X	X	X	X	X	X	X	X	X
443	X	X	X	X	X	X	X	X	X	X	X	X	X	X
453	X	X	X	X	X	X	X	X	X	X	X	X	X	X
463	X	X	X	X	X	X	X	X	X	X	X	X	X	X
483	X	X	X	X	X	X	X	X	X	X	X	X	X	X
503	X	X	X	X	X	X	X	X	X	X	X	X	X	X