

1.2162 PDF-2 **21MnCr5** **Comprimento: 500 mm**

Espessura: +0,4/-0 mm Comprimento: +15/-0 mm Largura: +3/-0mm

Estado de fornecimento: max. 217 HB

Análise química

C: 0,18 – 0,24 Cr: 1,0 – 1,3 Si: 0,15 – 0,35 Mn: 1,1 – 1,4 P: 0 – 0,03 S: 0 – 0,03

Espessura (mm)

Larg.	6,3	8,3	10,3	12,3	15,3	20,3	25,3	30,3	40,3	50,3
33	X	X	X	X	x	x	x	x		
43	X	x	x	X	x	X	x	x	x	
53	X	x	x	x	x	x	x	x	x	x
63	X	x	x	x	x	x	x	x	x	x
73	X	x	x	x	x	x	x	x	x	X
83	X	x	x	x	x	x	x	x	x	X
93	X	x	x	x	x	x	x	x	x	X
103	X	x	x	x	x	x	x	x	x	X
123	X	x	x	x	x	x	x	x	x	X
143	X	x	x	x	x	x	x	x	x	X
153	X	x	x	x	x	x	x	x	x	X
163	X	x	x	x	x	x	x	x	x	X
183	X	x	x	x	x	x	x	x	x	X
203	X	x	x	x	x	x	x	x	x	X
223	X	x	x	x	x	x	x	x	x	X
243	X	x	x	x	x	x	x	x	x	X
253	X	x	x	x	x	x	x	x	x	X
263	X	x	x	x	x	x	x	x	x	X
283	X	x	x	x	x	x	x	x	x	X
303	X	x	x	x	x	x	x	x	x	X
323	X	x	x	x	x	x	x	x	x	X
343	X	x	x	x	x	x	x	x	x	X
353	X	x	x	x	x	x	x	x	x	X
363	X	x	x	x	x	x	x	x	x	X
383	X	x	x	x	x	x	x	x	x	X
403	X	x	x	x	x	x	x	x	x	X
423	X	x	x	x	x	x	x	x	x	X
443	X	x	x	x	x	x	x	x	x	X
453	X	x	x	x	x	x	x	x	x	X
463	X	x	x	x	x	x	x	x	x	X
483	X	x	x	x	x	x	x	x	x	X
503	X	x	x	x	x	x	x	x	x	X