

1.2316 PDF-1 **X38CrMo16** comprimento: 300 mm

Espessura: + 0,4 / - 0 mm Comprimento: + 15 / - 0 mm Largura: + 3 / - 0 mm

Estado de fornecimento: max. 325 HB

Análise química

C: 0,33 – 0,45 Si: 0 – 1,5 Mn: 0 – 1,5 P: 0 – 0,03 S: 0 – 0,03

Cr: 15,5 – 17,5 Mo: 0,8 – 1,3 Ni: 0 – 1,0

Espessura (mm)

Larg.	8,3	10,3	12,3	15,3	20,3	25,3	30,3	40,3	50,3	60,3	70,3	80,3	90,3	100,3	120,3	140,3
33	X	X	X	X	X	X	X									
43	X	X	X	X	X	X	X	X								
53	X	X	X	X	X	X	X	X	X							
63	X	X	X	X	X	X	X	X	X	X						
73	X	X	X	X	X	X	X	X	X	X	X					
83	X	X	X	X	X	X	X	X	X	X	X	X				
93	X	X	X	X	X	X	X	X	X	X	X	X	X			
103	X	X	X	X	X	X	X	X	X	X	X	X	X			
123	X	X	X	X	X	X	X	X	X	X	X	X	X			
143	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
153	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
163	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
183	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
203	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
223	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
243	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
253	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
263	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
283	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
303	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X

* Largura e comprimento serrado: em bruto: + tolerância / - 0 mm