

1.2714 PDF-1 55NiCrMoV7 Comprimento: 500 mm

Espessura: +0,4/-0 mm Comprimento: +15/-0 mm Largura: +3/-0mm

Estado de fornecimento: max. 250 HB

Análise química

C: 0,5 – 0,6 Si: 0,1 – 0,4 Mn: 0 – 0,03 P: 0 – 0,03 S: 0 – 0,03
 Cr: 0,8 – 1,2 Mo: 0,35 – 0,55 Ni: 1,5 – 1,8 V: 0,05 – 0,15

Espessura (mm)

| Larg. | 8,3 | 10,3 | 12,3 | 15,3 | 20,3 | 25,3 | 30,3 | 40,3 | 50,3 | 60,3 | 70,3 | 80,3 | 90,3 | 100,3 | 120,3 | 140,3 | 150,3 |
|-------|-----|------|------|------|------|------|------|------|------|------|------|------|------|-------|-------|-------|-------|
| 33 | x | x | x | x | x | x | x | | | | | | | | | | |
| 43 | x | x | x | x | x | x | x | x | x | | | | | | | | |
| 53 | x | x | x | x | x | x | x | x | x | x | | | | | | | |
| 63 | x | x | x | x | x | x | x | x | x | x | x | | | | | | |
| 73 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | |
| 83 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | |
| 93 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | |
| 103 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | |
| 123 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | |
| 143 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | |
| 153 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 163 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 183 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 203 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 223 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 243 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 253 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 263 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 283 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |
| 303 | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x | x |