

1.2842/1.2510 PDF-2 **90MnCrV8/100MnCrW4** Comprimento: 1000 mm

Aço plano de precisão sem tolerância dimensional para maquinação

Espessura: +0,05 /-0 mm Comprimento: +15/-0 mm Largura: +0,2 /-0mm

Estado de fornecimento: max. 229 HB

Análise química

C: 0,85 – 0,95 Si: 0,1 – 0,4 Mn: 1,8 – 2,2 P: 0 – 0,03 Cr: 0,2 – 0,5

V: 0,05 – 0,2

Espessura (mm)

Larg.	1,0	1,5	2,0	3,0	4,0	5,0	6,0	8,0	10,0	12,0	15,0	16,0	18,0	20,0	25,0	30,0	40,0	50,0	60,0	
4,0					x															
5,0						x														
6,0							x													
8,0								x												
10,0	x	x	x	x	x	x	x	x	x											
12,0	x	x	x	x	x	x	x	x	x	x										
15,0	x	x	x	x	x	x	x	x	x	x	x									
16,0												x								
18,0													x							
20,0	x	x	x	x	x	x	x	x	x	x	x			x						
25,0	x	x	x	x	x	x	x	x	x	x	x			x	x					
30,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x				
35,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x				
40,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x			
50,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
60,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x	x	x
70,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
80,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
100,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
120,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
125,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
150,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
160,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
180,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
200,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
250,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		
300,0	x	x	x	x	x	x	x	x	x	x	x			x	x	x	x	x		