

**1.4122 PDF-1 X39CrMo17-1 Comprimento: 300 mm**

Espessura: + 0,4 / - 0 mm      Comprimento: + 15 / - 0 mm      Largura: + 3 / - 0 mm

Estado de fornecimento: max. 325 HB

Análise química

C: 0,33 – 0,45      Si: 0 – 1,0      Mn: 0 – 1,5      P: 0 – 0,045      S: 0 – 0,03  
 Cr: 15,5 – 17,5      Mo: 0,8 – 1,3      Ni: 0 – 1,0

Espessura (mm)

Larg.	8,3	10,3	12,3	15,3	20,3	25,3	30,3	40,3	50,3	60,3	70,3	80,3	90,3	100,3	120,3	140,3
33	x	x	x	x	x	x	x									
43	x	x	x	x	x	x	x	x								
53	x	x	x	x	x	x	x	x	x							
63	x	x	x	x	x	x	x	x	x	x						
73	x	x	x	x	x	x	x	x	x	x	x					
83	x	x	x	x	x	x	x	x	x	x	x	x				
93	x	x	x	x	x	x	x	x	x	x	x	x	x			
103	x	x	x	x	x	x	x	x	x	x	x	x	x	x		
123	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	
143	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
153	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
163	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
183	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
203	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
223	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
243	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
253	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
263	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
283	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x
303	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x	x